

<b>PRODUCT DATA SHEET</b>	
Quality Control	

Internal use <input type="checkbox"/>	External use <input type="checkbox"/>
---------------------------------------	---------------------------------------

<b>Customer:</b> SEPT SADEM SOFRAFILM		<b>Product Code:</b> -14124510	
<b>N.Ord.:</b>		<b>Date:</b> 06/07/2017	
<b>Description:</b> PE CAST BASSE DENSITÉ (LLDPE) TRANSPARENT			
Film Properties			
<b>Width:</b> 125 mm	<b>Thickness:</b> 0.023 mm	<b>Cling:</b>	<b>Inside</b> <input type="checkbox"/>
			<b>Outside</b> <input type="checkbox"/>
<b>Density</b> [g/cm <sup>3</sup> ]: ~ 0.919			

CARACTERISTIQUES MECANIQUES	SPECIFICATION					UNITE	METHODE D'ESSAI	TOLÉRANCE
	15μ	17μ	20μ	23μ	30μ			
<b>CHARGE A LA RUPTURE</b>						N/ mm <sup>2</sup>	ASTM D 882	10 %
<ul style="list-style-type: none"> <li>• Sens long</li> <li>• Sens travers</li> </ul>	28,0 16,0	29,0 17,0	30,0 19,0	32,0 20,0	35,0 23,0			
<b>RESISTANCE ADMISSIBLE</b>						N/ mm <sup>2</sup>	ASTM D 882	10 %
<ul style="list-style-type: none"> <li>• Sens long</li> <li>• Sens travers</li> </ul>	7,0 6,8	7,0 6,8	7,1 6,9	7,2 7,0	7,5 7,4			
<b>ALLONGEMENT A LA RUPTURE</b>						%	ASTM D 882	10 %
<ul style="list-style-type: none"> <li>• Sens long</li> <li>• Sens travers</li> </ul>	400 700	480 700	480 700	520 740	540 790			
<b>ALLONGEMENT MISE EN OEUVRE</b>	120	120	120	160	200	%	Méthode interne	10 %
<b>DART TEST</b>	60	60	80	95	110	gr	ASTM D 1709	10 %

**Mini bobine idéale pour le regroupement**

